

TEST REPORT

DATE: 04-10-2023	Page 1 of 1	TEST NUMBER : 0296309	
CLIENT	Loba-Wakol LLC - NC		
TEST METHOD CONDUCTED	ASTM D2047 James Machine - C	ASTM D2047 James Machine - Coefficient of Friction on Flooring	

Material

DESCRIPTION OF TEST SAMPLE		
IDENTIFICATION	Duo	
COLOR	Natural	
CONSTRUCTION	Finished Wood	

GENERAL PRINCIPLE

This test was used to measure the relative static coefficient of friction by using the James Machine.

TEST RESULTS

TEST ENVIRONMENT	69° F 50% Relative Humidity

Sensor Materials	Dry
Leather	0.65

APPROVED BY:

Gary asbury



This facility is accredited by the National Voluntary Laboratory Accreditation Program for the specific scope of accreditation under Lab Code 100297. This accreditation does not constitute an endorsement, certification, or approval by NIST or any agency of the United States Government for the producttested. This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples testedand is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory, Inc. shall not be used under any circumstance in advertising to the general public.



714 Glenwood Place

Dalton, GA 30721

706-226-3283

Fax: 706-226-6787

protest@optilink.us